

EMACO[®] CP 30 ANODE

Durable Anodic Conductive Coating for Reinforced Concrete Cathodic Protection (CP)

Description of Product

EMACO CP 30 ANODE is a unique, water based, one component anode coating specifically designed for steel reinforced concrete structures which are suffering ongoing corrosion damage, or require protection against future corrosion initiation. The material contains highly conductive coated fibres which provide superior current distribution and mechanical properties resulting in an enhanced anode life.

Fields of Application

Suitable applications include the control of active corrosion or the prevention of the onset of corrosion in:

- Bridges
- Highway structures
- Car parks
- Buildings

Features and Benefits

- Efficient electrical current distribution and high conductivity
- High adhesion
- Concrete compatibility
- Good vapour permeability
- Single component, ready to use
- Brush, roller or spray application
- No primer required
- Water-based, solvent free

Technical Data/Typical Properties

Anode Characteristics	
Maximum current density (concrete structure surface area), mA/m ²	20
Bulk resistivity, ohm.cm	<1
Typical physical properties ^(a)	
Wet density, kg/l	1.05
Solids content (by volume), % approximately	50
Water vapour permeability, μ	274
Bond strength (concrete substrate in-service value at 20 mA/m ²), N/mm ²	>1

^(a) Typical values: all tests carried out at 21°C unless otherwise stated

Tests and approvals

EMACO CP 30 ANODE has been tested by Taywood Engineering Limited, UK:
Evaluation Report 1303/94/7613

Application Procedure

Preparation of Substrate

Preparation of the concrete substrate is vital to achieve optimum performance and long service life from the cathodic protection installation. Remove all surface coatings, defective renders, foreign matter, formwork treatments, laitance, algae and other contaminants that may adversely affect the bond. Use abrasive blasting or high pressure water jetting. *Do not use vibrating or high impact methods*; such methods increase the risk of inducing micro cracks that may affect the adhesion and long-term durability of the anode system.

Spalled or delaminated areas and cracks should be repaired with approved EMACO[®] cathodic protection concrete repair products. Hairline cracks may be left untreated. Under no circumstances should any cracks be injected with materials, which will insulate areas from the CP system. Areas of low cover and exposed steel must be treated or the cover built up to that required.

Primary Anode^(b)

A primary anode is an essential requirement for a EMACO CP 30 ANODE system. The required number and configuration for correct current distribution will be project specific and is, therefore, a CP design decision. As a guide for a plane surface, primary anodes should be placed at 1.5m centres (maximum) with a 0.5m clearance from the edges of the anode zone.

The primary anode may be embedded in the EMACO CP 30 ANODE using an appropriate open gauze tape, which is laid over the primary anode and held in position with EMACO CP 30 ANODE. Alternatively, the primary anode may be fixed directly to the prepared substrate by an appropriate method, such as a series of individual dots of a fast setting adhesive. To protect the primary anode, overlay with a suitable non-woven fabric.



The Chemical Company

The configuration should allow the connection to the rectifier to be made outside the anodic zone and in duplicate as a minimum. Suitable primary anode materials include platinum/niobium-clad copper wire (0.8mm diameter)

^(b) Contact your BASF Construction Chemicals (UK) Ltd office for advice.

Mixing

EMACO CP 30 ANODE is supplied as a ready-to-use product and must not be diluted or altered in any way. Stir the material with a paddle mixer before application to ensure uniform dispersion of the solid content throughout the mixture.

For optimum results mixing should be carried out between 20 and 30°C.

Application

EMACO CP 30 ANODE may be applied using a brush, roller or suitable spray application technique ^(c). Roller and spray applications are recommended as they ensure optimum tridimensional distribution of the fibres throughout the anode coating.

Application should be carried out at ambient temperature, which should be a minimum of 10°C, and should not be undertaken when the ambient temperature is expected to fall below 5°C during the next 24hour period. The temperature of the substrate should be at least 3°C above the dew point to prevent condensation on the concrete surface.

Apply a first coat of EMACO CP 30 ANODE at the rate of at least 525 g/m² of concrete surface area. Whilst the first coat is still wet, embed the primary anode using the open gauze tape.

Alternatively, if the primary anode has been fixed directly to the concrete, apply the protective non-woven fabric to the primary anode using a little extra THORO[®] CP ANODE 30.

Do not apply the second coat until the first is completely dry. In any case, it should not be applied within 24 hours to allow the first coat to cure adequately.

The second coat of EMACO CP 30 ANODE should be applied at the rate of at least 525g/m² of concrete surface area.

EMACO CP 30 ANODE is not intended for applications involving continuous immersion in water or in tidal situations.

^(c) Contact your BASF Construction Chemicals (UK) Ltd office for advice.

Curing

Drying times primarily depend upon prevailing conditions such as wind, humidity and temperature. The recommended drying time is a minimum of 24 hours.

Overcoating

EMACO CP 30 ANODE can be overcoated with approved EMACO CP coating products to enhance performance in aggressive environments or for aesthetic purposes.

Operation maintenance of CP installation

To achieve cathodic protection of the reinforcement and optimise the service life of the CP system, especially the anode, it is essential that suitable design, commissioning, monitoring, control and maintenance procedures are followed. Reference should be made to the draft CEN Standard TC262/SC2/WG2.

Clean up

Clean equipment and spillages immediately with water. Dried material can be removed with xylene.

Coverage

Coverage is dependent upon various factors, including the method of working and substrate condition. The recommended dry-film thickness is 500µm, which is normally achieved in two layers and results in a theoretical coverage rate of 1.05kg/m² or 1litre/m² for a two-coat application.

Packaging

EMACO CP 30 ANODE is supplied pre-packed in 20 litre plastic pails.

Storage

EMACO CP 30 ANODE should be stored under cover and clear of the ground at a minimum temperature of 5°C. Do not stack more than 2 pails high. Once opened the material should be used immediately.

Shelf Life

Under normal conditions in unopened packaging the shelf life is 12 months.

BASF Construction Chemicals (UK) Ltd

PO Box 4

Earl Road

Cheadle Hulme

Cheadle

Cheshire

SK8 6QG

Tel: +44 (0) 161 485 6222

Fax +44 (0) 161 488 5220

www.basf-cc.co.uk



The Chemical Company

EMACO CP 30 ANODE BASF Construction Chemicals (UK) Ltd Version 6, July 2006

Health and Safety

*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

Solvent Based Products

Use in well-ventilated areas; avoid inhaling. Suitable respiratory equipment may be needed, eg when spraying. Can cause skin, eye irritation. Wear protective eye shields and gloves during use. Do not smoke or allow sparks or naked lights when stored or in use.

Powder Products

Should be handled to minimise dust formation; use light mask if excessive dust unavoidable. Cement powders when wet or moistened can cause burns to skin and eyes, which should be protected during use.

Resin Products

Can cause irritation, dermatitis or allergic reaction. Use protective equipment particularly for skin and eyes. Use only in well ventilated areas.

Spillage

Chemical products can cause damage; clean spillage immediately.

Disclaimer:

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.